

Declaration of Performance

Fibrin® XT

Low & Bonar nv
 Industriestraat 39
 9240 Zele, Belgium
 T: +44 1482 863777
 info@adfil.com

Factory code:	02	Class:	Ia
AVCP System:	3	Notified Lab:	1136

Intended use: for non-structural use in mortar, grout and concrete

Product code: M220P12-1812

Essential Characteristics	Performance	Tolerance	Standard
Length	13,0/19,0 mm	+/-1,5 mm	EN 14889-2:2006
Linear Density	3,5 dtex	+/-0,35 dtex	EN 14889-2:2006
Equivalent Diameter	22 µm	-0,9/+1,3 µm	EN 14889-2:2006
Tensile strength	380 MPa	-100 MPa	EN 14889-2:2006
Tenacity	42 cN/tex	-11,0 cN/tex	EN 14889-2:2006
Vebe time - 0,6kg	6,0 (5,7) s		EN 14889-2:2006
Vebe time - 0,75kg	n.p.d.		EN 14889-2:2006
Vebe time - 0,9kg	n.p.d.		EN 14889-2:2006
Vebe time - 0,91kg	6,3 (5,7) s		EN 14889-2:2006
Vebe time - 1,0kg	n.p.d.		EN 14889-2:2006
Vebe time - 1,2kg	n.p.d.		EN 14889-2:2006

- n.p.d. = no performance determined

The performance of the product identified above is in conformity with the declared performance in above table.

This declaration of performance is issued under the sole responsibility of

Zele, Belgium
 1/07/2013

Jeroen Smet
 Product Manager